



## Lightweight Concrete Filler (LCF) THE REVOLUTIONARY LOW DENSITY CEMENT

## **Product Description:**

**LCF** is a revolutionary, lightweight product made from Portland cement and proprietary expanded polystyrene foam aggregate. The aerated foam aggregate gives the cement a range of unique properties, making it perfect for deep fill applications. **LCF** is ready–mixed cement designed to be capped with a underlayment. **LCF** is mixed and pumped onsite with underlayment pumps making installation quick and easy.

## **Product Advantages:**

- Ultra-lightweight
- Density of 28-32 pcf
- Foam beads coated to prevent water absorption
- Not moisture sensitive
- Can be sloped
- No thickness limitation
- Fast drying
- Pours over conduit, wires, pipes, etc.
- Thermal properties

## **Technical Data:**

Function:	Low Density Fill for Deep Fill Applications
Density:	28 Day Dry Density: 28-32 pcf
Compressive Strength: (ASTM C109)	200-500 psi (1.3-3.4 m)
Flexural Strength: (ASTM C78)	119 psi
Mod of Elasticity: (ASTM C649)	1.1 GPa
Freeze/Thaw: (ASTM C666)	No loss @ 300 cycles
R-Value:	1.8 per inch

Level-Right LCF Bags	Water Demanded
1	2.0 – 2.2 gal (7.6 – 8.3 L)
2	4.0 – 4.4 gal (15.1 – 16.6 L)
3	6.0 – 6.6 gal (22.7 – 25.0 L)
4	8.0 – 8.8 gal (30.3 – 33.3 L)
5	10.0 – 11.0 gal (37.9 – 41.6 L)
6	12.0 – 13.2 gal (45.4 – 50.0 L)

Thickness	Yield per 40 lb. Bag
1/2"	36 ft2 (3.34 m2)
3/4"	24 ft2 (2.23 m2)
1"	18 ft2 (1.67 m2)
1 1⁄2"	12 ft2 (1.11 m2)
2"	9 ft2 (0.84 m2)
3"	6 ft2 (0.56 m2)
4"	4.5 ft2 (0.42 m2)
6"	3 ft2 (0.28 m2)

160 West Hintz Road Wheeling, Ilinois 60090 P: 847-520-4455 • F: 847-520-4970